

Materialdatenblatt / *material data sheet*

LD-PE transluzent / *ldpe translucent*



Materialbezeichnung / *material description*
LD-PE Regranulat transluzent / *ldpe regranulate translucent*

Artikel-Nr. / *order number*
LD-PE RE 5025 / 01

MFI: 0,5 - 1,2 (g/10 Min.) (190 ° C / 2.16 kg)
Dichte / *density:* 0,920 - 0,935 (g/cm³)

Diese Werte wurden an statistisch repräsentativen Mustern auf Basis von Proben für diese Charge ermittelt, ohne dass sie als Eigenschaft zugesichert werden. Die MFI-Bestimmung wird nach DIN EN ISO 1133-1 geprüft und die Dichte nach DIN ISO 1183-1.

Das Werkprüfzeugnis entbindet den Abnehmer nicht von der Eingangskontrolle.

These values are a statistically representative sample, determined from the basis shown by this charge, without these properties being guaranteed. The MFI determination is proved following DIN EN ISO 1133-1 and the density following DIN ISO 1183-1.

The plant certification doesn't remove the recipient from the responsibility of incoming inspection.

Angaben ohne Gewähr
No responsibilities is taken for the correctness of this information