

Materialdatenblatt / *material data sheet*

PE-PP bunt / *pe-pp coloured*



Materialbezeichnung / *material description*

PE-PP Regranulat weiß / *pe-pp regranulate coloured*

Artikel-Nr. / *order number*

PE-PP RE 3301

MFI: 0,5- 3,0 (g/10 Min.) (190 ° C / 2.16 kg)

MFI: 2,0 - 9,0 (g/10 Min.) (230 ° C / 2.16 kg)

Dichte / *density*: 0,910 - 0,960 (g/cm³)

Diese Werte wurden an statistisch repräsentativen Mustern auf Basis von Proben für diese Charge ermittelt, ohne dass sie als Eigenschaft zugesichert werden. Die MFI-Bestimmung wird nach DIN EN ISO 1133-1 geprüft und die Dichte nach DIN ISO 1183-1.

Das Werkprüfzeugnis entbindet den Abnehmer nicht von der Eingangskontrolle.

These values are a statistically representative sample, determined from the basis shown by this charge, without these properties being guaranteed. The MFI determination is proved following DIN EN ISO 1133-1 and the density following DIN ISO 1183-1.

The plant certification doesn't remove the recipient from the responsibility of incoming inspection.

Angaben ohne Gewähr

No responsibilities is taken for the correctness of this information